

# InstaCote OH Primer

**OH Primer** is a fast drying silane based primer which can be used on metal or concrete surfaces. OH Primer may also be used to assist in drying up light amounts of surface moisture on concrete surfaces.

## Typical Physical Properties

	WET
Solids	
By Weight	10%
VOC	795 g/l
Coverage	1 gallon - 400 to 500 sq.ft. @ 1 mil
Dry time 25° C	1/2 to 1 hour (can vary slightly)
Recoat	24 hours
Shelf life	Indefinite if sealed after use
Thinner	Never Recommended

Used on the following substrates: Metals, Steel, Concrete and Silica Exposed Surface

Recommended method of applying: Spray, brush or brush on

Application: Lightly mist or apply OH Primer onto surfaces to be coated. Try to avoid applying too much primer. If this happens wipe up excess primer with a cloth towel and reapply to that area if needed. The primer will be dry and ready to apply a top coating in fifteen (15) minutes.

Recoat time: After the primer is dry (15 minutes) you have up to four (4) hours to top coat after which you must re-apply the primer.

InstaCote, Inc.  
160 C. Lavoy Rd.  
Erie, Michigan, USA 48133  
Phone (734) 847-5260  
Fax (734) 847-9008  
Email: tom.nachtman@instacote.com